

IN THE SPECIFICATION

Please amend Table 2 as shown below.

Table 2

	1*	2	3	4*	5	6	7*	8*	9*	10	11*	12	13	14*	15[[[*]]]	16
PPO I	100	100	100	-	-	-	50	50	50	50	80	80	80	67	67	67
PPO II	-	-	-	100	100	100	-	-	-	-	-	-	-	-	-	-
HIPS	-	-	-	-	-	-	50	50	-	-	-	-	-	23	-	-
XPS	-	-	-	-	-	-	-	-	42.5	42.5	-	-	-	-	19.5	19.5
SEBS	-	-	-	-	-	-	-	-	7.5	7.5	-	-	-	-	3.5	3.5
Polysalicylate	-	4	6	-	4	6	-	2.5	-	2.5	-	2	4	-	-	3
Irganox 1010	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
LLDPE	-	-	-	-	-	-	-	-	-	-	-	-	-	1	1	1
Glass	-	-	-	-	-	-	-	-	-	-	20	20	20	-	-	-
RDP	-	-	-	-	-	-	-	-	-	-	-	-	-	9	9	9
Tensile strength at break	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-	-
Unaged	84	84	82	79	80	81	52	50	55	56	120	115	110	64	70	77
120°C	82	92	89	40	72	75	44	38	53	60	102	102	106	68	73	82
140°C	72	84	86	35	63	70	35	29	48	56	89	95	105	62	71	79
175°C	65	86	84	-	-	-	-	-	-	-	60	73	92	53	65	75
190°C	32	70	81	-	-	-	-	-	-	-	-	-	-	-	-	-

*Comparative examples